



127 Village Lane
 Easley, SC 29642-8961
 Phone (864) 605-0150
 Fax (864) 605-0830
 www.tru-flo.com

<i>BUTTERFLY VALVE SEAT MATERIAL PROPERTIES</i> Property	EPDM	NEOPRENE	VITON	SILICONE
Temperature	-55 to 275°F	-40 to 225°F	-20 to 400°F	-80 to 450°F
Acid Resistance	Good-Excellent	Good	Good	Good
Alkali Resistance	Good-Excellent	Fair-Good	Poor-Good	Poor-Good
Petroleum Oil Resistance	Poor	Excellent	Excellent	Good
Vegetable Oil Resistance	Good	Good	Excellent	Good
Abrasion Resistance	Good-Excellent	Good	Good	Good-Excellent
Compression Set	Fair	Good	Good-Excellent	Good-Excellent